



GUANGZHOU MATEYS CHEMICALS LTD.

CR-203W Darkish Hard Chrome Plating Additive

1. Specifications

- (1) Perfect dispersing
- (2) Excellent deep plating skill
- (3) Bright black & uniform
- (4) High hardness
- (5) Perfect wear resistance as white Chrome

2. Composition & Conditions

Composition	Range
Chromiumtrioxide(CrO ₃)	400-500 g/l
CR-203W	20-25 g/l
Temperature	20-30℃
Current density	10-50A/dm ²
The anode	Sn alloy (6-8%)

Remarks. Pls kindly give us an email for more details.

ADD: 25 Jianhua Rd., Tianhe Software Park, Keyun Rd.,

Tianhe Dist., Guangzhou, China510665

TEL: +86 20 85576176/85555261/85555262

CEL: +86 13922181787 Skype: gzmateys

Email: gzmateys@qq.com gzmateys@163.com

URL: www.gzmateys.com/en gzmateys.en.alibaba.com